

SUBMITTAL

Golden Glow FSK

DESCRIPTION

Golden Glow building insulation is a light density thermal and acoustical fibre glass insulation bonded with thermo-setting resin. This flexible insulation will not stain nor corrode metal studs, rot or sustain fungi or vermin. **Golden Glow** will not shrink nor settle from vibration, exposure, temperature or humidity.

FSK-Faced building insulation is manufactured using a three part foil/skrim/kraft vapor retarder adhered to the fibre glass batt. Tabs or flanges are provided at the edges for taping to the face or inside of the stud. The FSK facing has a vapor transmission (perm) rating of 0.05 or less. OFI FSK faced batts comply with ASTM C665, Type III, Class A. FSK batts are designed for use where a Class A flame spread rating (25 or less) is required.

USES

Golden Glow FSK faced batts are designed for use where the facing will be left exposed. The three part facing is tough and can resist impact more than other facings. **Golden Glow FSK** is easy to install and can be used in both vertical and horizontal applications and in both new and retrofit construction projects.

ADVANTAGES

Golden Glow FSK faced batts have good body and recovery to ensure thermal performance in all applications. Easy to cut with a knife to fit around a variety of surfaces, **Golden Glow FSK** faced batts have tabs that fold out to tape to the face or to the inside of studs. **Golden Glow FSK** faced batts have a fire hazard classification of 25/50 and can be left exposed.



Golden Glow FSK faced batts are an excellent economical component of any building with long life performance and virtually no maintenance. **Golden Glow FSK** faced batts reflect light and absorb sound. The vapor barrier has an effective 0.05 or less perm rating (ASTM E-96-A).

LIMITATIONS

Local building codes.

CODES, STANDARDS, RATINGS & LISTINGS

Golden Glow FSK faced batts comply with ASTM C665, Type III, Class A, and ASTM E 84-98 (Federal specification HH-I-521F has been cancelled and replaced by ASTM C655).

The FSK has a vapor transmission (perm) rating of 0.05 or less (ASTM E-96-A).

SUBMITTAL

Golden Glow FSK

ESTIMATING, ORDERING & SPECIFYING DATA

FSK Faced Batts (Type III, Class A)				FSK Faced Batts (Type III, Class A)			
R-value	Dimension	PCS/Bag	Sq Ft/bag	R-value	Dimension	PCS/Bag	Sq Ft/bag
R11	3.50" x 16" x 96"	11	117.33	R19	6.25" x 24"x 96"	6	96.00
R11	3.50" x 24" x 96"	11	176.00	R30	10.0" x 16"x 48"	10	53.33
R19	6.25" x 16" x 96"	6	64.00	R30	10.0" x 24"x 48"	10	80.00

N.B. For skews not shown above, please contact your distributor/agent for details on availability/minimum orders.

SPECIFICATION

When specifying **Golden Glow** state the R-value and the designation "**FSK faced batts**".

OFI INSULATION FAMILY

Golden Glow FSK Faced Batts are just one member of OFI's "Insulation Family", including **Golden Glow** Kraft faced, unfaced, Foil faced and Noise Control batts, OFICinetile, OFIVERSATILE ceiling panels, QuickPak, and OFI Commercial/Industrial Insulations.

SUBMITTED TO:	_____
SUBMITTED BY:	_____
DATE:	_____
JOB REFERENCE:	_____
JOB NAME:	_____



Ottawa Fibre Inc.

For more information: Telephone: (613) 247-7116 Facsimile: (613) 736-7281